

PAULOWNIA

OUR PAULOWOOD



DESCRIPTION OF THE WOOD

- Sapwood: White.
- Heartwood: Greyish yellow with pink highlights
- Wood Fibers: Straight. No knots.
- Wood Grain: Fine and smooth

PHYSICAL PROPERTIES*


- Apparent density at 12% humidity 270 Kg/m³.
Very light wood.
- Dimensional stability
 - Volumetric contraction coefficient 0.14 %.Little nervous wood.
 - Higrscopicity of 0,0027 Kg/m³

PAULOWNIA LOGS

Thanks to its high flash point, its excellent compressive strength index, its insulating properties, paulownia is widely used in the construction sector, for the construction of houses, floors, load-bearing structures, poles, beams, ceilings, coatings, upholstery materials, fixtures, doors and any furniture.

MEASURES

Length: According to customers'



GLOBAL TIMBER GROUP